

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 June 2004 (24.06.2004)

PCT

(10) International Publication Number
WO 2004/053020 A1

(51) International Patent Classification⁷: **C09K 19/46**,
19/02

(21) International Application Number:
PCT/EP2003/012952

(22) International Filing Date:
19 November 2003 (19.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02027739.8 11 December 2002 (11.12.2002) EP

(71) Applicant (for all designated States except US): **MERCK
PATENT GMBH** [DE/DE]; Frankfurter Strasse 250,
64293 Darmstadt (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FRANCIS,
Matthew** [GB/GB]; 21 Stratford Place, Eastleigh SO50
4NB (GB). **GOULDING, Mark, John** [GB/GB]; 50

Seymour Road, Ringwood, Hampshire BH24 1SH (GB).
JONES, John, Clifford [GB/GB]; The Old Granary
Crowcroft, Leighsinton WR13 5ED (GB). **BELDON,
Steve** [GB/GB]; Bridge Street 35, Ledbury Herefordshire
HR8 2AH (GB).

(74) Common Representative: **MERCK PATENT GMBH**;
Frankfurter Strasse 250, 64293 Darmstadt (DE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

[Continued on next page]

(54) Title: FAST SWITCHING LIQUID CRYSTAL COMPOSITIONS FOR USE IN BISTABLE LIQUID CRYSTAL DEVICES





Illustration of zenithal bistability using grating alignment
(with the lines indicating the local director) showing a) the high tilt
(continuous) and b) the low tilt (defect) states.



The a) VAN and b) TN geometries for ZBD showing the
director distribution of the high and low tilt states.

(57) Abstract: The invention is directed to the use
of a fast switching liquid crystal composition said
composition comprising at least 30 weight% of a
component (α) containing one or more compounds
having a dielectric anisotropy $\Delta\epsilon$ of at least 25,
whereby at least 25 weight% of said compounds
have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and
at least 5 weight% of a component (δ) containing
one or more compounds having a ratio of γ_1/T_{NI}^K of
0.51 mPa-s/K or less, a clearing point T_{NI} of at least
100°C and a rotational viscosity γ_1 of not more than
190 mPa-s (wherein γ_1 is the rotational viscosity
at 20 °C in mPa-s and T_{NI}^K is the clearing point in
degrees Kelvin); in a bistable liquid crystal device
and especially in a zenithal bistable nematic liquid
crystal device, a nematic liquid crystal medium, and
a bistable liquid crystal device comprising said fast
switching liquid crystal composition.

JC09 Rec'd PCT/PTO 10 JUN 2005

**Fast switching liquid crystal compositions for use in bistable liquid
crystal devices**

5 The invention is directed to the use of a fast switching liquid crystal composition in a bistable liquid crystal device and especially in a zenithal bistable nematic liquid crystal device, a nematic liquid crystal medium, and a bistable liquid crystal device comprising the fast switching liquid crystal composition.

10 Electrooptical devices utilizing liquid crystal media for displaying information are well known and used in a wide variety of technical applications (see, for a review, H. Kawamoto, Proc. IEEE, 90, 460 (2002)). Among these, nematic liquid crystal devices are the most prominent; there are, for instance, twisted nematic (TN) liquid crystal devices (M. Schadt and W.

15 Helfrich, Appl. Phys. Lett., 18, 127 (1971)) and super-twisted nematic (STN) liquid crystal devices (see, inter alia, T.J. Scheffer and J. Nehring, Appl. Phys. Lett., 48, 1021 (1984)). These devices are monostable, i.e. the liquid crystal medium is switched to an ON state by application of a suitable voltage, and is allowed to switch to an OFF state when the voltage applied

20 falls below a lower voltage level. In order to display complex information electrooptical devices need to comprise a number of picture elements that can be switched independently of each other. However, when direct or even multiplex addressing of pixels are used, the number of elements addressable in nematic liquid crystal displays is limited, in the first case by

25 mere geometrical requirements of the electrical connections and in the second case by the steepness of the device's transmission versus the voltage curve.

30 This limitation can be overcome by incorporating thin film transistors (TFT) into each picture element. Such devices, also known as active matrix (AM) displays, enable addressing of a high number of picture elements and thus

of large area high resolution displays and with relatively low voltage requirements. Some of these devices are also mechanically rather stable and have a wide temperature range. Although this allows the construction of small and portable battery powered displays, for certain applications the techniques has several drawbacks. Manufacturing AM displays is still a
5 complicated process involving the building up of a complex assembly which contributes to rather high costs of production. Since the device has no intrinsic or internal memory, constant update of the display even for static images is required. This causes relatively high power consumption and,
10 hence, rather poor battery life time. This is especially undesired with portable devices displaying information that is changed only from time to time or in a limited part of the display such as mobile phones, personal digital assistants (PDAs), pagers, electronic shelf edge labels, and the like.

15 An approach to avoid the limitations and drawbacks of these nematic liquid crystal devices is to use displays with an internal memory effect, e.g. a bistable liquid crystal device. Bistability means that the molecules of the liquid crystal medium inside the device can adopt two (or more) different stable states. Consequently, by applying a suitable addressing scheme the
20 liquid crystal molecules of the medium are switched into a first stable state which persists even after addressing; utilization of another addressing scheme causes the liquid crystal molecules to adopt a second stable state that likewise persists after addressing.

25 Ferroelectric liquid crystal displays using smectic liquid crystal materials can be made into bistable devices. They have, however, several disadvantages, e.g. lack of shock resistance, narrow operating temperature range, and low cell gap causing manufacturing difficulties. Therefore, these ferroelectric devices are unlikely to fulfill the requirements to displays for
30 the portable devices mentioned above.

However, not only ferroelectric smectic liquid crystals are capable of being used in bistable devices but also nematic liquid crystals. Besides other approaches that utilize bistable bulk configurations adopted by nematic liquid crystals (see, for instance, I. Dozov *et al.*, "Recent improvements of bistable nematic displays switched by anchoring breaking (BiNem[®])", Proceedings SID 01 (2001), 16.1, 224 and references therewithin), a promising way of achieving bistability in a nematic liquid crystal display is to use a surface alignment which can support two or more stable states. As discussed in literature (see, for instance, J.C. Jones, G. Bryan-Brown, E. Wood, A. Graham, P. Brett and J. Hughes, "Novel bistable liquid crystal displays based on grating alignment", in "Liquid Crystal Materials, Devices, and Flat Panel Displays", R. Shashidhar, B. Gnade, Eds., Proceedings of SPIE Vol. 3955 (2000), 84 and references cited therein) two types, azimuthal and zenithal bistability, can be distinguished.

In the first instance (i.e. azimuthal bistability), the director of the liquid crystal molecules in the display having a grating alignment on the surface of one of the display cell's plates (or substrates) will lie parallel to said plate in both stable states; that means that switching between the stable states occurs within the plane of the display cell's plates (see, for instance, WO 92/00546 and WO 95/22077 which describes the use of a substrate having a bigrating alignment layer). However, reproducing selection of the stable states is found to be difficult and switching generally requires a high switching voltage.

On the other hand, zenithal bistability is observed when the zenithal bistable surface is used (see Figure 1; the tiny lines represent the local director of the liquid crystal molecules that are oriented by interaction with the surface grating and appropriate alignment layer). With such a surface, the director of the liquid crystal molecules has two possible configurations with different pretilt angles in the same azimuthal plane (i.e. the plane

perpendicular to the surface of the display cell's substrate). The first state is the high tilt state while the second state is the low tilt state. The grating of the zenithal bistable surface is defined by its amplitude a and its pitch L ; typical values are for L of about $1\ \mu\text{m}$ and for a of about 0.6 to $0.8\ \mu\text{m}$ (see
5 WO 97/14990 and, for more details, WO 02/08825; and J.C. Jones, G. Bryan-Brown, E. Wood, A. Graham, P. Brett and J. Hughes, "Novel bistable liquid crystal displays based on grating alignment", in "Liquid Crystal Materials, Devices, and Flat Panel Displays", R. Shashidhar, B. Gnade, eds., Proceedings of SPIE Vol. 3955 (2000), 84).

10 A homeotropic orientation can be, for example, induced by coating the grating with a homeotropic alignment layer; this orientation ensures that the director of the liquid crystal molecules does not lie parallel to the grooves of the grating. Although the orientation of the director of the liquid crystal
15 molecules is perpendicular to the (local) surface, i.e. varying with the location on the surface along a direction perpendicular to the grooves, the orientation in the "bulk" is very much influenced by the opposite surface alignment in both states. Switching from one stable state to the other may be achieved by applying a simple electrical pulse thereby causing a switch
20 from a black display or picture element to a white one (or vice versa) with the appropriate polariser configuration and retardation, and switching back to the original state occurs upon application of a pulse of opposite polarity thereby causing a switch from white to black (or vice versa). Switching may also be induced by using pulses of same polarity but with much higher
25 voltages (also referred to as "reverse switching"); however, reverse switching is a detrimental effect which limits the operation of a zenithal bistable nematic device in terms of the addressing and so a high a voltage as possible is desired for the reverse switching.

In general, for obtaining zenithal bistability only one of the two display cell's substrates is provided with a surface grating. The opposite plate may have a surface providing a homeotropic alignment of the liquid crystal director (VAN mode, see Figure 2a)) or a surface inducing planar alignment of the director (twisted mode, see Figure 2b)) thereby causing the twisting of the liquid crystal director around the axis perpendicular to the substrates across the cell for the low tilt state. For details with regard to cell geometry and configuration, exact cell parameters, addressing means, assembling of the entire zenithal bistable device (including use of polarisers) and so on, see the disclosure of WO 97/14990, E.L. Wood, G.P. Bryan-Brown, P. Brett, A. Graham, J.C. Jones, and J.R. Hughes, "Zenithal Bistable Device (ZBDTM) Suitable for Portable Applications, SID 00 Digest (2000), 124, J.C. Jones, J.R. Hughes, A. Graham, P. Brett, G.P. Bryan-Brown, and E.L. Wood, "Zenithal Bistable Devices: Towards the electronic book with a simple LCD", IDW '00 (2000), 301, J. C. Jones, S. M. Beldon and E. L. Wood, "Greyscale in Zenithal Bistable LCD: The Route to Ultra-low Power Colour Displays", seminar talk on the ASID meeting 2002 of the Society for Information Display, Singapore, September 2002; and the detailed discussion given in J.C. Jones, G. Bryan-Brown, E. Wood, A. Graham, P. Brett and J. Hughes, "Novel bistable liquid crystal displays based on grating alignment", in "Liquid Crystal Materials, Devices, and Flat Panel Displays", R. Shashidhar, B. Gnade, eds., Proceedings of SPIE Vol. 3955 (2000), 84, and references cited therein.

Utilizing zenithal bistability in electrooptical devices offers attractive features:

- Image retention on a display without continuous update combined with
- High mechanical shock stability
- Low power consumption since the display only needs addressing when the image changes

- Infinite multiplexibility for unlimited resolution without the need for TFT elements
- Transmissive and reflective modes possible
- Suitability for use with plastic substrates

5

Besides the assembly and make up of the zenithal bistable display, another key issue to the zenithal bistable device technology is the nematic liquid crystal medium used inside the display's cell.

10

The zenithal bistable device and hence the liquid crystal medium have to meet several requirements more or less depending on the specific use of the device. Since there is no consistent theory so far that might predict the physical variables to be optimized, it turned out to be helpful using a set of (semi-)empirical parameters for evaluating liquid crystal media with respect

15

to their usefulness in zenithal bistable nematic devices. These are illustrated in the so-called τ -V curve for switching voltages of pulse duration τ and for 10 and 90% switching levels with opposite polarities (see figure 3) for a liquid crystal mixture of the prior art, namely MLC-6204-000 of Merck KGaA, Darmstadt, Germany.

20

Firstly, in order to minimize power consumption, to allow more flexibility with the addressing of the device's picture elements and to remain within the limits of standard STN drivers a low *switching field* and correspondingly a low *operating voltage* is desirable for switching from one bistable state to the other. For material comparison one can determine the switching field E for a pulse (usually a 100 μ s pulse duration) from the switching voltage V that gives a transmission change from, e.g., 0 to 90% transmission (black-to-white; B-W) for a particular liquid crystal mixture in a given test cell providing zenithal bistability. (In general, one can also use the 100 to 10% transmission change transition of white-to-black, W-B, where the switching field of which may be higher or lower than the B-W transition depending on

25

30

the grating's shape and dimensions.) In order to take into account the voltage drop across the grating (which varies for different types of gratings as well as cell thickness) the value of E actually measured is corrected to distinguish the field just across the liquid crystal again for comparison purposes giving the *corrected switching field* $E_{LC@100\mu s}$ for a 100 μs pulse. Here, an additional factor of 1.5 μm is added to the cell thickness d when calculating the field just across the liquid crystal:

$$E_{100\mu s} = V_{100\mu s} / d \text{ and } E_{LC@100\mu s} = V_{100\mu s} / (d + 1.5) \text{ where } d \text{ is in } \mu m.$$

Multiplying $E_{LC@100\mu s}$ with *optimum cell gap* d_{opt} (that can be approximated by using the TN 1st minimum condition $d_{opt} = \lambda \sqrt{3} / (2\Delta n)$ with $\lambda = 555 \text{ nm}$ and Δn being the optical anisotropy of the liquid crystal medium) gives the *operating voltage* V_{opt} corresponding to the optimum cell gap for a 100 μs pulse for just the liquid crystal. $E_{LC@100\mu s}$ and so V_{opt} depend on the liquid crystal medium used. (The optimum cell gap is considered only for the twisted mode (see Figure 2b)) here but comparisons can also be made for the VAN mode (see Figure 2a)), where the retardation of the hybrid state will be matched to either a half-wave plate or quarter-wave plate depending on the polariser configuration ($d\Delta n = \lambda/2$ and $d\Delta n = \lambda/4$, respectively).

The second empirical parameter that needs to be taken into account is the *operating window* ΔV_{opt} corresponding to the optimum cell gap. It describes the effect of reverse switching: When applying a pulse with a given time slot of, e.g. 400 μs , and a defined pulse polarity, e.g. B-W, one observes the desired switching at a specific value of the switching field and a further reverse switching (e.g. W-B in this case) which is not induced by a pulse of inverse polarity but by a pulse of the same polarity at an increased switching field. For technical purposes, obviously said operating window ought to be as wide as possible to permit more flexibility of the driving schemes used and particularly in relation to achieving good grayscale

operation (see J. C. Jones, S. M. Beldon and E. L. Wood, "Greyscale in Zenithal Bistable LCD: The Route to Ultra-low Power Colour Displays", seminar talk on the ASID meeting 2002 of the Society for Information Display.) It can be represented by $\Delta E_{LC@400\mu s}$, that is the corrected
 5 difference between the 90% reverse switching field and the 90% B-W switching field for a 400 μs pulse:

$$\Delta E_{400\mu s} = \Delta V_{400\mu s} / d \text{ and } \Delta E_{LC@400\mu s} = \Delta V_{400\mu s} / (d + 1.5) \text{ where } d \text{ is in } \mu m.$$

10 Taking into account the optimum cell gap d_{opt} by multiplying with $\Delta E_{LC@400\mu s}$ eventually gives the operating window ΔV_{opt} ($d_{opt}\Delta E_{LC@400\mu s} = \Delta V_{opt}$).

Still another parameter of great importance is the *clearing point* T_{NI} of the liquid crystal medium describing the temperature at which the nematic
 15 mixture becomes isotropic. For many technical purposes and for increasing the variability of electrooptical devices utilizing zenithal bistability (and so the possible applications), liquid crystal media having a high clearing point, preferably of at least 80 °C or more, are desired.

20 A further parameter, the *optical response time* τ_{opt} corresponding to the optimum cell gap, describes how fast the liquid crystal medium changes between stable states upon application of an electric pulse. It can be determined by measuring the response time τ for the 10-90 % B-W transition using a 100 μs pulse in the actual test cell; then, in order to
 25 normalize the experimental values, τ is multiplied by $(d_{opt}/d)^2$ giving τ_{opt} (with d_{opt} being the optimum cell gap as calculated above for V_{opt} and d being the actual cell gap of the test cell used). The W-B transition is much faster (less than 1ms) and so indeed the B-W response time is of most importance when assessing the properties of the liquid crystal medium
 30 used. The smaller τ_{opt} the faster the optical response of the liquid crystal medium. A small τ_{opt} (of about 40 ms or, preferably, less than about 30 ms)

may be desirable for certain electrooptical applications, e.g. displaying moving pictures. It is even more preferred for specific video applications that τ_{opt} is less than about 16 ms so as not to observe flash.

5 Those liquid crystal media the use of which in zenithal bistable devices have been described in the prior art do not meet all the parameter requirements outlined above. Even liquid crystal mixture MLC-6204-000 (available from Merck KGaA, Darmstadt, Germany) that has been used in zenithal bistable devices as the preferred medium (WO 01/40853, Example
10 6; J.C. Jones, G. Bryan-Brown, E. Wood, A. Graham, P. Brett and J. Hughes, "Novel bistable liquid crystal displays based on grating alignment", in "Liquid Crystal Materials, Devices, and Flat Panel Displays", R. Shashidhar, B. Gnade, Eds., Proceedings of SPIE Vol. 3955 (2000), 84) has a clearing point T_{NI} of only 62.4 °C that is rather low for use in zenithal
15 nematic bistable device for many possible applications. Furthermore, its τ_{opt} is above 40 ms that is rather high for use in zenithal nematic bistable device for some specific applications requiring a small optical response time τ_{opt} .

20 The present invention therefore encounters the problem to provide a liquid crystal composition that is suitable for use in a bistable liquid crystal device and especially in a zenithal bistable nematic device and has an improved set of properties.

25 The problem is solved by the use of a liquid crystal composition in a bistable liquid crystal device, said device being preferably a zenithal nematic liquid crystal device, whereby said composition comprises

- at least 30 weight% (based on the total weight of the composition) of a component (α) containing one or more compounds having a
30 dielectric anisotropy $\Delta\epsilon$ of at least 25,
whereby at least 25 weight% (based on the total weight of the

composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and

- a component (δ) containing one or more compounds each having a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s (wherein γ_1 is the rotational viscosity at 20 °C in mPa·s and T_{NI}^K is the clearing point in degrees Kelvin).

(The dielectric anisotropy, the rotational viscosity and the clearing point can be determined according to the methods described in "Physical Properties of Liquid Crystals – Description of the measurement methods", ed. W. Becker, Merck KGaA, Darmstadt, 1998, whereby values for single compounds may be extrapolated from those determined using a known concentration (usually 10 weight% of the single compound) in a standard host mixture (usually ZLI-4792 of Merck KGaA, Darmstadt, Germany) for which the initial mixture values are also known. Further parameters of single compounds may be obtained similarly.)

A further subject matter of this invention is a bistable liquid crystal device comprising

- two outer substrates which, together with a frame, form a cell;
 - a liquid crystal composition present in said cell;
 - electrode structures with alignment layers on the inside of said outer substrates whereby at least one alignment layer comprises an alignment grating that permits the liquid crystal composition to adopt at least two different stable states whereby the assembly of said electrode structures with said alignment layers being such that a switching between the said at least two different stable states is achieved by applying suitable electric signals to said electrode structures;

- whereby said liquid crystal composition is said liquid crystal composition as described above and below and that comprises said components (α) and (δ).

5 In particular, said bistable liquid crystal device is a zenithal bistable nematic liquid crystal device in which said electrode structures with alignment layers on the inside of said outer substrates have at least one alignment layer that comprises an alignment grating that permits the compounds of said liquid
10 crystal composition to adopt at least two different stable states with different pretilt angles in the same azimuthal plane whereby the assembly of said electrode structures with said alignment layers being such that a switching between the said at least two different stable states is achieved by applying suitable electric signals to said electrode structures.

15 It will be acknowledged that the invention is described hereinafter primarily with regard to the use of the liquid crystal composition above in a zenithal bistable nematic liquid crystal device although it may be used in other liquid crystal devices as well, for instance, in bistable liquid crystal devices like azimuthal bistable liquid crystal devices as disclosed, inter alia, in WO
20 92/00546 and WO 95/22077. Thus, details are given for the zenithal bistable nematic liquid crystal device but can easily be adapted to the requirements of other types of bistable liquid crystal devices.

25 The zenithal bistable nematic device and the liquid crystal composition for use in a zenithal bistable nematic device according to the invention show an improved set of parameters said parameters being, inter alia, operating voltage, operating window, and, especially, clearing point. It should be noticed that, for instance, the clearing point of the liquid crystal compositions for use in the zenithal bistable nematic devices of the
30 invention is significantly higher than the clearing point of liquid crystal mixtures previously used in zenithal bistable nematic devices. Operating voltage and operating window are both in a range useful for operating of a

zenithal bistable nematic device. Furthermore, in the preferred
embodiments of the invention the optical response time τ_{opt} is decreased
significantly so that fast switching liquid crystal compositions for use in
bistable liquid crystal devices and especially in zenithal bistable nematic
5 liquid crystal devices are obtained.

The cell that is part of the zenithal bistable nematic device according to the
invention may be any conventional cell which allows the nematic liquid
crystal composition to adopt at least two different zenithal bistable states.
10 Two possible stable states are schematically depicted in Figure 1. The two
different zenithal bistable states are characterized by two different pretilt
angles that are adopted by the liquid crystal molecules in the same
azimuthal plane. The cell comprises a frame and two outer substrates or
plates and has electrode structures with alignment layers on the inside of
15 said substrates. At least one of these alignment layers has an zenithal
alignment grating known to those skilled in the art and as described, for
instance, in WO 97/14990, WO 01/40853, WO 02/08825, and J.C. Jones,
et al., Proceedings of SPIE Vol. 3955 (2000), 84.

20 The electrode structures are assembled with the alignment layer(s) in such
a way that (in the case of two stable states) switching from one stable state
to the other can be achieved by applying suitable electric signals to the
electrode structures thereby applying said electric signals to the liquid
crystal composition inside the cell. Commonly, single pulses can be used
25 as such suitable electric signals. Details are known to the artisan and
described in WO 97/14990, WO 01/40853, WO 02/08825, J.C. Jones, J.R.
Hughes, A. Graham, P. Brett, G.P. Bryan-Brown, IDW '00 (2000), 301, J.C.
Jones, et al., Proceedings of SPIE Vol. 3955 (2000), 84, and E. L. Wood,
P. J. Brett, G. P. Bryan-Brown, A. Graham, R. M. Amos, S. Beldon, E.
30 Cubero and J. C. Jones, "Large Area, High Resolution Portable ZBD
Display", SID 02 Digest (2002), 22-25.

The substrate opposite to the substrate having the grating alignment layer may have an homeotropic alignment due to suitable surface treatment (see Figure 2a)). Switching upon application of an electric pulse occurs from the high tilt or vertically aligned state to the low tilt or hybrid aligned state. This switch gives a black-to-white (B-W) change if the cell is placed between crossed polarizers (at 45° to the grating direction), with the brightest white state obtained when the vertically aligned state acts as a half-waveplate ($d\Delta n = \lambda/2$). This switching mode is called *VAN mode*. Zenithal bistable devices utilizing the VAN mode are very insensitive to cell gap variations. They require additional optical compensators to achieve wide viewing angles. A second switching mode of zenithal bistable devices is called *TN mode* (see Figure 2b)): The substrate opposite to the substrate having the grating alignment layer has a alignment layer, usually of rubbed polyimide, causing planar alignment of the liquid crystal molecules on said substrate. This in turn causes the twisting of the liquid crystal director around their axis perpendicular to the substrates across the cell. Switching upon application of an electric pulse now occurs from the low tilt or twisted aligned state to the high tilt or hybrid aligned state. This switch gives a black-to-white (B-W) change if the cell is placed between parallel polarizers and using the slightly modified TN 1st minimum condition (as given above) accounting for the influence of the ordinary refractive index of the hybrid state. Due to a high normal incidence contrast ratio additional optical compensators for achieving wide viewing angles are not required in a transmissive display. Therefore the TN mode is preferred for most of the technical applications of zenithal bistable nematic devices. It is also possible to build up a zenithal bistable reflective display and even a zenithal bistable transfective display. For details, also with regard to the polarizers used, it is referred to WO 97/14990, E.L. Wood, G.P. Bryan-Brown, P. Brett, A. Graham, J.C. Jones, and J.R. Hughes, SID 00 (2000), 124, and E. L. Wood, P. J. Brett, G. P. Bryan-Brown, A. Graham, R. M.

Amos, S. Beldon, E. Cubero and J. C. Jones, "Large Area, High Resolution Portable ZBD Display" SID 02 Digest (2002), 22-25.

5 In the context of the present invention and with respect to the compounds contained in the liquid crystal composition for use in bistable liquid crystal devices and especially in zenithal bistable nematic devices of the invention the term "alkyl" means - as long as it is not defined in a different manner elsewhere in this description or the claims - straight-chain and branched hydrocarbon (aliphatic) radicals with 1 to 15 carbon atoms; the hydrocarbon
10 radicals may be unsubstituted or substituted with one or more substituents being independently selected from the group consisting of F, Cl, Br, I or CN. This subclass of "alkyl" containing aliphatic saturated radicals may also be designated as "alkanyl". Furthermore, "alkyl" is also meant to comprise unsubstituted or likewise substituted hydrocarbon radicals in which one or
15 more of the CH₂ groups are such replaced by -O- ("alkoxy", "oxaalkyl"), -S- ("thioalkyl"), -CH=CH- ("alkenyl"), -C≡C- ("alkinyl"), -CO-O- or -O-CO- that there are no adjacent hetero atoms (O, S). Preferably, alkyl is a straight-chain or branched saturated hydrocarbon having 1, 2, 3, 4, 5, 6, 7 or 8 carbon atoms and being unsubstituted or mono- or poly-substituted with F.
20 More preferably, alkyl is meant to be methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, n-pentyl, neopentyl, n-hexyl, n-heptyl, n-octyl; CF₃, CHF₂, CH₂F; CF₂CF₃. Most preferably, alkyl is a straight-chain hydrocarbon of up to 8 carbon atoms.

25 Since one or more CH₂ groups of an alkyl radical may be replaced by -O- as described above, the term "alkyl" also comprises "alkoxy" and "oxaalkyl" moieties. "Alkoxy" means "O-alkyl" in which the oxygen atom is directly linked to the group or ring being substituted with alkoxy and alkyl is defined as above. In particular, "alkyl" in "O-alkyl" means methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, n-pentyl, neopentyl, n-hexyl, n-heptyl or n-octyl, whereby alkyl is optionally substituted with F. Most preferably, alkoxy
30

is -OCH₃, -OC₂H₅, -O-n-C₃H₇, -O-n-C₄H₉, -O-t-C₄H₉, -OCF₃, -OCHF₂,
-OCHF or -OCHFCHF₂. In the context of the present invention the term
"oxaalkyl" comprises alkyl moieties in which at least one non-terminal CH₂
group is replaced by O in such a way that there are no adjacent oxygen
atoms. Preferably, oxaalkyl comprises straight-chain radicals of the formula
5 C_tH_{2t+1}-O-(CH₂)_u- in which t and u are independently of each other 1, 2, 3,
4, 5 or 6; especially t is 1 or 2 and u is an integer from 1 to 6.

If one or more of the CH₂ groups of alkyl are replaced by sulfur a "thioalkyl"
10 radical is obtained. Thioalkyl comprises alkyl moieties in which at least one
terminal or non-terminal CH₂ group is replaced by S (sulfur) in such a way
that there are no adjacent sulfur atoms. Preferably, thioalkyl comprises
straight-chain radicals of the formula C_tH_{2t+1}-S-(CH₂)_u- in which t is 1, 2, 3,
4, 5 or 6 and u is 0, 1, 2, 3, 4, 5 or 6; especially t is 1 or 2 and u is zero or
15 an integer from 1 to 6.

In the context of the present invention the term "alkenyl" means an alkyl
radical in which one or more -CH=CH- moieties are present. When two
-CH=CH- moieties are present the radical may also be designated as
20 "alkadienyl". An alkenyl radical may comprise 2 to 15 carbon atoms and
may be straight-chain or branched. It can be unsubstituted or mono- or
polysubstituted with F, Cl, Br, I or CN; one or more of its CH₂ groups may
be replaced independently of each other by -O-, -S-, -C≡C-, -CO-O-,
-OC-O- such that there are no hetero atoms adjacent to each other. If the
25 alkenyl CH=CH moiety is not a terminal CH₂=CH group it may exist in two
configurations, namely the E-isomer and the Z-isomer. In general, the E-
isomer (trans) is preferred. Preferably, alkenyl contains 2, 3, 4, 5, 6 or 7
carbon atoms and means vinyl, 1E-propenyl, 1E-butenyl, 1E-pentenyl, 1E-
hexenyl, 1E-heptenyl, 2-propenyl, 2E-butenyl, 2E-pentenyl, 2E-hexenyl,
30 2E-heptenyl, 3-butenyl, 3E-pentenyl, 3E-hexenyl, 3E-heptenyl, 4-pentenyl,

4Z-hexenyl, 4E-hexenyl, 4Z-heptenyl, 5-hexenyl and 6-heptenyl. More preferred alkenyl is vinyl, 1E-propenyl, 3E-butenyl.

In the case one or more CH_2 alkyl groups are replaced by $-\text{C}\equiv\text{C}-$ an alkynyl radical is obtained. Also the replacement of one or more CH_2 alkyl groups by $-\text{CO}-\text{O}-$ or $-\text{O}-\text{CO}-$ is possible. The following of these radicals are preferred: acetyloxy, propionyloxy, butyryloxy, pentanoyloxy, hexanoyloxy, acetyloxymethyl, propionyloxymethyl, butyryloxymethyl, pentanoyloxymethyl, 2-acetyloxyethyl, 2-propionyloxyethyl, 2-butyryloxyethyl, 2-acetyloxypropyl, 3-propionyloxypropyl, 4-acetyloxybutyl, methoxycarbonyl, ethoxycarbonyl, propoxycarbonyl, butoxycarbonyl, pentoxycarbonyl, methoxycarbonylmethyl, ethoxycarbonylmethyl, propoxycarbonylmethyl, butoxycarbonylmethyl, 2-(methoxycarbonyl)ethyl, 2-(ethoxycarbonyl)ethyl, 2-(propoxycarbonyl)-ethyl, 3-(methoxycarbonyl)-propyl, 3-(ethoxy-carbonyl)-propyl oder 4-(methoxycarbonyl)-butyl.

The liquid crystal composition for use in the (zenithal) bistable (nematic) liquid crystal device of the invention contains at least two different components, component (α) and component (δ).

20

It has been found by the inventors that the liquid crystal composition for use in a bistable liquid crystal device needs to comprise a component (δ) which may influence the optical response time τ_{opt} as desired. This component (δ) contains one or more compounds each having a ratio of $\gamma_1/T_{\text{NI}}^{\text{K}} \leq 0.51 \text{ mPa}\cdot\text{s/K}$, a clearing point $T_{\text{NI}} \geq 100 \text{ }^\circ\text{C}$ and a rotational viscosity $\gamma_1 \leq 190$ (wherein γ_1 is the rotational viscosity at $20 \text{ }^\circ\text{C}$ in $\text{mPa}\cdot\text{s}$ and T_{NI}^{K} is the clearing point in degrees Kelvin).

25

It is preferred that component (δ) contains at least one compound having a ratio of $\gamma_1/T_{\text{NI}}^{\text{K}}$ of $0.46 \text{ mPa}\cdot\text{s/K}$ or less, a clearing point T_{NI} of at least $110 \text{ }^\circ\text{C}$ and a rotational viscosity γ_1 of not more than $180 \text{ mPa}\cdot\text{s}$. It is even more


30

preferred that the ratio of γ_1/T_{NI}^K is 0.42 mPa·s/K or less, the clearing point T_{NI} is of at least 120 °C and the rotational viscosity γ_1 of said compound is of not more than 175 mPa·s.

- 5 Component (δ) may be present in an amount of about 5 weight% (based on the total weight of the composition) but usually not more than about 65 weight%. It is preferred that its amount is in the range from about 7 to about 50 weight%, more preferred in the range from about 10 to about 35 weight%.

10

It is further preferred that said component (δ) comprises at least one compound of formula I



I


15

in which

R^{11} and R^{12} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

20


25



is



or



in which

L^{11} and L^{12} are independently of each other H or F; and


30



is



or




in which



L^{13} and L^{14} are independently of each other H or F.

Preferred compounds of formula I are compounds of one of the formulas I-A to I-I



5





10





15



20



25





30

wherein m and r are independently of each other 2, 3, 4, 5, 6 or 7, n and q are independently of each other 1, 2, 3, 4, 5, 6 or 7, and p is 4, 5, 6, 7 or 8.

More preferred are compounds of formulas I-A and I-B, i.e. compounds of formula I in which R^{11} is alkenyl with up to 7 carbon atoms or alkadienyl with up to 8 carbon atoms, R^{12} is alkanyl with up to 7 carbon atoms, the ring indicated by A is a cyclohexyl ring, and the ring indicated by B is a phenyl ring. Also, compounds of formulas I-D, I-E, I-G, I-H and I-I are likewise preferred. Especially preferred are compounds of formula I-A with m being 2, 3, 4 or 5 and n being 1, 2, 3 or 4.

Specific examples of compounds according to formula I are the following:





with I1 and I3 being the most preferred ones.

15

The following table, Table 1, shows the values of γ_1 (in mPa·s), T_{NI} (in degrees Celsius, °C) and γ_1/T_{NI}^K (in mPa·s/K) for some specific examples of compound I that is preferably comprised by component (δ).

20



Table 1

Compound	γ_1 / mPa·s	T_{NI} / °C	γ_1/T_{NI}^K / mPa·s/K
I1	118	161	0.27
I3	159	181	0.35
I5	118	192	0.25
I6	100	175	0.22
I7	149	190	0.32
I8	154	124	0.39
I9	174	138	0.42
I10	157	265	0.29
I11	94	220	0.19
I12	88	116	0.23
I13	111	154	0.26

30

The other component required according to the invention, component (α), contains one or preferably more compounds having a high dielectric anisotropy $\Delta\epsilon$ of 25 or more, especially of 30 or more. At least 25 weight%, preferably 30 weight% or more, (based on the total weight of the composition) of the compounds of component (α) exhibit a dielectric anisotropy $\Delta\epsilon$ of 40 or more. At least 30 weight% (based on the whole composition) of component (α) need to be comprised by the liquid crystal composition of the zenithal bistable nematic device according to the invention. It is preferred that the liquid crystal composition comprises 35 weight% or more, even more preferred at least 40 weight%, still more preferred at least 45 weight%, most preferred 50 weight% or more, of said component (α).

It is preferred that said component (α) comprises at least one compound of formula II and/or at least one compound of formula III



in which

a, b, c and d are independently of each other 0, 1, 2, 3 or 4;

R^{21} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-\text{O}-$, $-\text{S}-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{CO}-\text{O}-$, $-\text{OC}-\text{O}-$ such that there are no hetero atoms adjacent to each other;


R^{31} is C_2-C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C \equiv C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Z^{21} and Z^{31} are independently of each other a single bond or -C \equiv C-.


It has been found by the inventors that component (α) preferably comprises either one or more compounds of formula II or one or more compounds of formula III or one or more compounds of both formula II and formula III (besides other compounds having the required high dielectric anisotropy that may be present). In one preferred embodiment of the invention component (α) contains at least one compound of formula II but no compound of formula III; in another preferred embodiment component (α) contains at least one compound of formula III but no compound of formula II. If component (α) contains at least one compound of formula II, said compound(s) of formula I may be present in a total amount of at least 5 weight%, preferably at least 10 weight%, more preferred at least 15 weight% or more. If component (α) contains one compound of formula III, said compound of formula II may be present in an amount of about 5 to 30 weight%, preferably 8 to 25 weight%, more preferred 10 to 20 weight%. However, if component (α) contains more than one compound of formula III, the total amount of these compounds is in the range of about 5 to about 55 weight%, preferably about 8 to about 35 weight%, more preferred about 9 to about 25 weight%.

With regard to compounds of formula II a and b may be independently of each other 0, 1, 2, 3 or 4, preferably 0, 1 or 2; that means that preferably each of the phenyl rings of formula II may be unsubstituted or mono- or disubstituted with fluorine. If present the F substituent(s) may be in any


position of the phenyl ring substituted. It is preferred that



5



and/or are independently of one another




with

L^{21} and L^{22} being independently of one another H or F. Furthermore, Z^{21} can be either a single bond (so that the CN group is directly linked to the phenyl ring) or a C-C triple bond thereby forming a $-C\equiv C-CN$ substituent of the phenyl ring. It is preferred that Z^{21} is a single bond.

10


Preferred compounds of formula II are the following compounds:

15




II-A

20




II-B











II-C

25



II-D


30



with R^{21} being defined as above. Preferably, R^{21} in formulas II and II-A to II-M is a straight-chain alkyl radical, especially an alkanyl radical with 1, 2, 3,

4, 5 or 6 carbon atoms. Highly preferred compounds are of general formula II-A1 with $n = 1, 2, 3, 4, 5$ or 6 .

5




II-A1


10

Especially preferred examples of compounds of formula II being present in component (a) either alone or in combination with each other are the following compounds of formula II1 to II3:

15




II1



II2

20



II3

25


It is preferred to have a mixture of all three compounds II1, II2 and II3 in the liquid crystal composition. For instance, compound II1 exhibits a dielectric anisotropy $\Delta\epsilon$ of 37.5 whereas compound II3 has a $\Delta\epsilon$ of 36.0.

30



With regard to compounds of formula III c and d may be independently of each other 0, 1, 2, 3 or 4, preferably 0, 1 or 2; that means that preferably each of the phenyl rings of formula III may be unsubstituted or mono- or di-substituted with fluorine. If present the F substituent(s) may be in any

position of the phenyl ring substituted. It is preferred that

5



and/or are independently of one another




with

L^{31} and L^{32} being independently of one another H or F. Furthermore, Z^{31} can be either a single bond (so that the CN group is directly linked to the phenyl ring) or a C-C triple bond thereby forming a $-C\equiv C-CN$ substituent of the phenyl ring. It is preferred that Z^{31} is a single bond.

10


Preferred compounds of formula III are the following compounds:

15




III-A

20




III-B

25




III-C




III-D

30



with R^{31} being defined as above. Preferably, R^{31} in formulas III and III-A to III-M is a straight-chain alkenyl radical, especially with 1, 2, 3, 4, 5 or 6 carbon atoms and most preferred with a terminal C=C double bond. Highly preferred compounds are of general formula III-B1 with $n = 2, 3, 4, 5$ or 6.

5




III-B1

10


Especially preferred examples of compounds of formula III being present in component (α) either alone or in combination with each other are the following compounds of formula III1 to III4:

15




III1

20




III2

25



III3

30




III4

The most preferred compound of formula III is compound III4 which exhibits a dielectric anisotropy $\Delta\epsilon$ of 59.5.

It will be acknowledged that other compounds than those of formulas II and III may be present in component (α) as long as they have a sufficiently high dielectrical anisotropy $\Delta\epsilon$ and are not detrimental to the set of parameters as outlined above.

Thus, it is preferred that component (α) of the liquid crystal composition used in the zenithal bistable nematic device of the invention also comprises one or especially more compounds of formula IV



in which

e and f are independently of each other 0, 1, 2, 3 or 4;

R^{41} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other (which means that R^{41} does not comprise any alkenyl radical);

Z^{41} is a single bond or $-C\equiv C-$.

With regard to compounds of formula IV e and f may be independently of each other 0, 1, 2, 3 or 4, preferably 0, 1 or 2; that means that preferably each of the phenyl rings of formula IV may be unsubstituted or mono- or di-substituted with fluorine. If present the F substituent(s) may be in any

5

position of the phenyl ring substituted. It is preferred that

10


and/or  are independently of one another

L^{41} and L^{42} being independently of one another H or F. Furthermore, Z^{41} can be either a single bond (so that the CN group is directly linked to the phenyl ring) or a C-C triple bond thereby forming a $-C\equiv C-CN$ substituent of the phenyl ring. It is preferred that Z^{41} is a single bond.

15


Preferred compounds of formula IV are the following compounds:

20




IV-A

25




IV-B




IV-C


30




IV-D




IV-E




IV-F




IV-G




IV-H




IV-J



IV-K



IV-L




IV-M

5


with R^{41} being defined as above. Preferably, R^{41} in formulas IV and IVA to IV-M is straight-chain alkyl, especially straight-chain alkanyl having 1, 2, 3, 4, 5, 6, 7 or 8 carbon atoms. Highly preferred compounds are of general formulas IV-A1 and IV-B1 with $n = 1, 2, 3, 4, 5$ or 6, whereby compounds of formula IV-A1 are most preferred.

10



IV-A1

15




IV-B1


20

Especially preferred compounds of formula IV are compounds of formula IV1 to IV6:

25




IV1




IV2


30




IV3



IV4




IV5



IV6

Among these compounds of formulas IV1 (having a dielectric anisotropy $\Delta\epsilon$ of 53.7), IV2, IV3 ($\Delta\epsilon = 44.9$) and IV4 ($\Delta\epsilon = 43.0$) are most preferred. If present the total amount of compounds of formula IV in the liquid crystal composition for use in the zenithal bistable nematic devices of the invention may be about 10 weight% or more (although even smaller amounts are possible as well), preferably 20 weight% or more, more preferred in the range of about 25 to 60 weight%, still more preferred in the range of about 35 to about 55 weight%. When used as a mixture different compounds of formula IV may be contained in component (α) in an almost equal amount. For instance, if compounds of formulas IV1 to IV4 are used, they may be contained in an 1:1:1:1 ratio.

In another preferred embodiment of the invention component (α) of the liquid crystal composition for use in the zenithal bistable nematic devices comprises at least one compound of formula XV:




XV

in which

j is 0 or 1;

R^{151} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


5 Z^{151} and Z^{152} are independently of each other a single bond or -C≡C-;




in which


L^{151} , L^{152} , L^{153} and L^{154} are independently of each other H or F.

25 Preferred classes of compounds comprised by formula XV are compounds of formula XV-A to XV-E in which Z^{151} is a single bond:







XV-B



XV-C




XV-D




XV-E

in which R^{151} is defined as above and preferably means a straight-chain alkyl with 1 to 8 carbon atoms, especially a straight-chain alkanyl or alkenyl having 2, 3, 4, 5 or 6 carbon atoms; Z^{152} is a $C\equiv C$ triple bond or preferably a single bond; and L^{151} , L^{152} , L^{153} and L^{154} are H or F with L^{151} and L^{152} being preferably H. Preferred compounds of formulas XV-A to XV-E are




XV-A1




XV-A2

5




XV-A3

10




XV-B1




XV-B2

15




XV-B3

20




XV-C1




XV-C2

25




XV-C3


30




IX-D1



IX-D2




IX-E1




IX-E2

in which R^{151} is as defined above.


Some specific examples of compounds of formula XV are




XV1



XV2




XV3




XV4

If these compounds are present in component (α) their total amount may range from about 5 to about 45 weight%. It is preferred that only one type of compounds of formulas XV-A to XV-E are present in the liquid crystal composition for use in the invention for the same time.


In a further preferred embodiment of the invention the liquid crystal composition for use in a bistable liquid crystal device and especially in a zenithal bistable nematic liquid crystal device may also comprises a component (β). Said component (β) may be present in the liquid crystal composition in an amount of at least 5 weight% or more. Component (β) may positively influence the clearing point of the liquid crystal compositions used in bistable liquid crystal devices, i.e. the clearing point may be increased by adding component (β). Component (β) comprises compounds of formula V and/or formula VI and/or formula VII and/or formula VIII and/or formula IX




V




VI



VII



VIII



IX


in which

g is 0 or 1;

R^{51} , R^{52} , R^{61} , R^{62} , R^{71} , R^{72} , R^{81} , R^{82} , R^{91} and R^{92} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;




L^{51} is H or F;

Z^{61} is $-CO-O-$, $-CH_2O-$, $-OCH_2-$, $-CF_2O-$, $-OCF_2-$, $-CH_2CH_2-$, $-CF_2CF_2-$, $-CH_2CF_2-$, $-CF_2CH_2-$, $-CH=CH-$ or $-C\equiv C-$;



are independently of each other


or




in which

L^{52} and L^{53} are independently of each other H or F.

Preferred compounds of formula V are of the following formulas:






with R^{51} and R^{52} being as defined above. Preferably, in formulas V and V-A to V-G R^{51} and R^{52} are both independently of each other straight-chain alkyl, more preferred straight-chain alkanyl or alkenyl having 2, 3, 4, 5 or 6 carbon atoms, especially straight-chain alkanyl with 2 to 6 carbon atoms, a is 1 and L^{51} is H or F (for formula V). Highly preferred compounds are of formula V-D and V-E. Especially preferred examples of formula V are compounds of formula V1 to V6:








20 Most preferred compounds of formula V are compounds V2, V4 and V6, and it is preferred to have a mixture of all three compounds in the liquid crystal composition.




25 With respect to formula VI preferred compounds are of formulas VI-A and VI-B in which g is 1 as well as of formulas VI-C and VI-D in which g is zero:











with R^{61} , R^{62} and Z^{61} being as defined above; Z^{61} is preferably -CO-O- or, in case of formula VI-D, -OCH₂-. R^{61} and R^{62} are preferably both independently of each other straight-chain alkyl, more preferred straight-chain alkanyl or alkenyl having 2, 3, 4, 5 or 6 carbon atoms, especially straight-chain alkanyl with 2 to 6 carbon atoms. Compounds of formula VI-B are more preferred. Especially preferred examples of formula VI are compounds of formulas VI1 to VI3 as well as of formulas VI4 and VI5 and of formulas VI6 to VI8:





It is especially preferred to have a mixture of compounds VI1, VI2 and VI3 in the liquid crystal composition.



Preferably, in formula VII R^{71} is straight-chain alkyl, especially straight-chain alkanyl having 2, 3, 4, 5 or 6 carbon atoms, and R^{72} is straight-chain alkyl or, more preferred, alkoxy having 1, 2, 3 or 4 carbon atoms. Especially preferred examples of formula VII are compounds of formula VII1 to VII6:






in which n is an integer from 1 to 6, preferably 2, 3 or 4, especially 3.


Preferred compounds of formula VII are compounds of formula VII2, VII4 and VII6 with $n = 3$ (giving an n -propyl substituent). It is preferred to have a mixture of all three compounds VII2, VII4 and VII6 in the liquid crystal composition.

Preferably, in formula VIII R^{81} is straight-chain alkenyl, especially straight-chain alkenyl having 2, 3, 4 or 5 carbon atoms, and R^{82} is straight-chain alkanyl or alkoxy both having 1, 2, 3, 4 or 5 carbon atoms (formula VIII-A or VIII-B with $n = 2, 3, 4, 5$ and $m = 1, 2, 3, 4, 5$).



Preferred compounds of formula VIII are compounds of formula VIII1 to VIII4:







VIII4

- 5 Especially preferred are compounds of formula VIII1, VIII3 and VIII4. They may be used alone or, more preferred, as a mixture of two or three compounds.

10 Regarding compounds of formula IX specific compounds are of the following formulas




IX-A




15

IX-B



IX-C




20


IX-D

with R^{91} and R^{92} being as defined above. Preferably, R^{91} and R^{92} are straight-chain alkyl, especially alkanyl, with 1, 2, 3, 4, 5 or 6 carbon atoms. Preferred compounds of formula IX are:

25




IX-C1



30

IX-D1

with n and m being independently of each other 1, 2, 3, 4, 5 or 6. Especially preferred examples of compounds of formula IX are



15 Component (β) may be used in an amount of 5 weight% or more in the liquid crystal composition for use in bistable liquid crystal devices according to the invention. When component (α) comprises at least one compound of formula III, it is preferred that the liquid crystal composition comprises 8


20 weight% or more of component (β). When there is no compound of formula II in component (α), an amount of at least 10 weight% of component (β) is even more preferred. In certain embodiments of the invention a total amount of 15 or 20 or more weight% of component (β) is highly preferred.

25 In an actual embodiment of the invention component (β) may contain one or more compounds of only one of the formulas V or VI or VII or VIII or IX. It is also possible that it contains one or more compounds of two, three or more of the formulas V to IX. It may contain an equal or a different amount of compounds of each formula used. It is preferred that component (β)

30 contains one or more compounds of one or two of the formulas V, VI, VII, VIII or IX. If compounds of two of the formulas V to IX are contained, any combination is possible. Both types of compounds may be used in an equal

amount, or one of the types may be used in an excess with regard to the other one, for instance, in a ratio of 2:1. It is preferred that an equal amount of both types of compounds is used. When component (α) comprises no compound of formula II, it is preferred that component (β) comprises compounds of two of the formulas V, VI, VII, VIII or IX.

In another preferred embodiment of the invention the liquid crystal composition for use in the bistable liquid crystal device and especially in the zenithal bistable nematic device according to the invention further comprises 3 weight% or more of a component (γ) containing one or more compounds having an optical anisotropy Δn of at least 0.20. It has been found that the use of this component (γ) may decrease the operating voltage V_{opt} of the liquid crystal composition. In general, component (γ) can comprise any (mesogenic) compound exhibiting a Δn of at least 0.20 that is not detrimental to the set of parameters important for use in especially zenithal bistable nematic liquid crystal devices. It is preferred that component (γ) comprises tolanes having a Δn of at least 0.20, especially at least one tolane compound of formula X:




in which

25 k is 0, 1 or 2;


R^{101} and R^{102} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced by -O-, -S-, -CH=CH-, -C \equiv C-, -CO-O-, -OC-O- such that there

30 are no hetero atoms adjacent to each other; and


- 48 -





Especially preferred are compounds of formula X-A



in which n and m are independently of each other 1, 2, 3, 4, 5 or 6 and k is 0, 1 or preferably 2. Preferred examples are of formula X-A1 with n being 2, 3 or 4 and m being 1, 2, 3, 4 or 5:





Among these compounds X-A1a and X-A1b are most preferred:



It should be noted that certain compounds of formula X as well as compounds having a structure similar to that of formula X in that R¹⁰² is replaced by a fluorine atom may also have a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s. Those may be comprised by component (δ). Among these compounds are, for instance, the compound of formula X-A1b ($\gamma_1/T_{NI}^K = 0.16$; $T_{NI} = 219$ °C; and $\gamma_1 = 81$ mPa·s); and the compound having a structure similar to structure X-A1b in which the butyl substituent on the right-hand ring has been replaced by F ($\gamma_1/T_{NI}^K = 0.19$; $T_{NI} = 189$ °C; and $\gamma_1 = 89$ mPa·s).

If present component (γ) is contained in an amount of at least 3 weight% and more preferred at least 5 weight%. Even much higher amounts of, e.g., up to 50 weight% of component (γ) may be used in specific embodiments of the invention in order to achieve, for instance, very fast switching.

The liquid crystal composition for use in the bistable liquid crystal devices and especially in the zenithal bistable nematic liquid crystal devices of the invention may comprise further substances for adjusting several properties of said composition if desired. For example, some of these substances may be used for adjusting the viscosity of the liquid crystal composition. (Hence, if one of these compounds has a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s, it may be a compound being comprised by component (δ).) In certain embodiments the liquid crystal composition for use in the zenithal bistable nematic devices according to the invention comprises at least one compound of formula XI and/or at least one compound of formula XII and/or at least one compound of formula XIII and/or at least one compound of formula XIV



in which

15 R^{111} and R^{142} are independently of each other C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


20 R^{121} , R^{131} , R^{132} and R^{141} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

25 R^{122} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


30

Y^{111} is F or Cl;

L^{111} and L^{112} are independently of each other H or F; and




and




are independently of each

other




or



10 The exact nature and amount of these compounds within the liquid crystal composition depend on the specific mixture and the desired effect and can be easily chosen by the skilled person.


Preferred compounds of formula XI are compounds of formula XI-A or XI-B

15




XI-A

20



XI-B




XI-C

25


with n being 2, 3, 4, 5 or 6 and Y^{111} being F or Cl. Especially preferred compounds of formula XI are the following compounds:


30



The most preferred compound of formula XI is compound XI1.


Preferred compounds of formula XII are compounds of formula XIIA, XIIB, XIIC, XIID, XIIE and XIIF:






XII D

5



XII E


10



XII F


with n being 1, 2, 3, 4, 5 or 6 and m being 1, 2, 3, 4, 5 or 6. Specific examples of compounds of formula XII are the following compounds:

15




XII 1

20




XII 2




XII 3

25




XII 4

30




XII 5




XII6

5




XII7




XII8

10




XII9

15




XII10



XII11


20

Preferred compounds of formula XIII are compounds of formula XIII A or XIII B:



XIII A


25




XIII B

30


with n being 1, 2, 3, 4, 5, 6, 7 or 8 and m being 1, 2, 3, 4, 5 or 6. Especially preferred examples of compounds of formula XIII are the following compounds:




Preferred compounds of formula XIV are compounds of formula XIVA




with n being 1, 2, 3, 4, 5, 6, 7 or 8 and m being 2, 3, 4, 5 or 6. Specific examples of compounds of formula XIV are the following compounds:





XIV4




XIV5

5

The most preferred compound of formula XIV is compound XIV2.


The liquid crystal composition for the use according to the invention in the bistable liquid crystal devices may also comprises mesogenic substances having a medium dielectric anisotropy of $\Delta\epsilon$ of about 8 to 10 or more, for instance one or more compounds of formula XVI and/or one or more compounds of formula XVII, preferably in an amount of up to 30 weight%, more preferred of up to 20 weight%:

15



XVI

20



XVII

25

in which

R^{161} and R^{171} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;


30

Y^{161} and Y^{171} are independently of each other F, Cl, C_1 - C_{15} alkanyl or C_2 - C_{15} alkenyl that are mono- or poly-substituted with halogen, or C_1 - C_{15} alkoxy, which is mono- or poly-substituted with halogen;

5 L^{161} and L^{171} are independently of each other H or F; and
 Z^{161} is $-CO-O-$, CH_2O or CF_2O .


Preferably these compounds are of formulas XVI-A, XVI-B and XVII-A, respectively:

10




XVI-A

15



XVI-B

20







XVII-A

with n being in all three formulas 1, 2, 3, 4, 5, 6 or 7. These substances may influence both the operating voltage and the operating window of the liquid crystal composition for use in the zenithal bistable nematic devices of the invention as desired.

The liquid crystal composition for the use according to the invention in the zenithal bistable nematic liquid crystal devices may also comprises one or more of the mesogenic substances according to the following formulas XVIII to XXII. The exact nature and amount of these compounds within the

30

liquid crystal composition depend on the specific mixture and the desired effect and can be easily chosen by the skilled person.



wherein

25 R^{181} , R^{182} , R^{201} , R^{211} and R^{221} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -
30 $C\equiv C$ -, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


R¹⁹¹

is C₁-C₁₅ alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH₂ groups may be replaced independently of each other by -O-, -S-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other (i.e. R¹⁹¹ does not represent an alkenyl radical);

L¹⁹¹, L¹⁹², L²⁰¹, L²⁰², L²⁰³, L²⁰⁴, L²¹¹, L²¹², L²¹³, L²¹⁴, L²¹⁵, L²¹⁶, L²²¹, L²²², L²²³ and L²²⁴ are independently of each other H or F; and

Y¹⁹¹, Y²⁰¹, Y²¹¹ and Y²²¹ are independently of each other F, Cl, C₁-C₁₅ alkanyl or C₂-C₁₅ alkenyl that are independently of each other mono- or poly-substituted with halogen, or C₁-C₁₅ alkoxy which is mono- or poly-substituted with halogen.



Preferred compounds of formula XVIII are of the formula XVIIIA



XVIII A






with n being 1, 2, 3, 4, 5, 6 or 7 and p being 2, 3, 4, 5, 6 or 7. More preferred are compounds of formula XVIIIA with n being 1, 2, 3, 4 or 5 and p being 2, 3, 4 and 5; especially preferred C_nH_{2n+1} is methyl, ethyl or n-propyl and C_pH_{2p-1} is a -CH₂-CH₂-CH=CH₂ or -CH₂-CH₂-CH=CH-CH₃ radical the latter preferably with *E*-configuration of the C=C double bond.


Preferred compounds of formula XIX are of the formulas XIXA and XIXB:



- 10 with n being 1, 2, 3, 4, 5, 6 or 7 and Y^{191} being F, Cl, CF_3 or OCF_3 . More preferred are compounds of formula XIXB with n being 2, 3, 4, 5, 6 or 7 and Y^{191} being F.


Preferred compounds of formula XX are of the formulas XXA to XXG:





XXF

5




XXG


with n being 1, 2, 3, 4, 5, 6 or 7 and Y^{201} being F, Cl, CF_3 or OCF_3 . More preferred are compounds of formulas XXB, XXC and XXD with n being 2, 3, 4, 5, 6 or 7 and Y^{201} being F.

Preferred compounds of formula XXI are of the formulas XXIA to XXIJ:

15




XXIA




XXIB

20




XXIC

25







XXID

30





XXIE



with n being 1, 2, 3, 4, 5, 6 or 7 and Y^{211} being F, Cl, CF_3 or OCF_3 . More preferred are compounds of formula XXID with n being 2, 3, 4, 5, 6 or 7 and Y^{211} being F.

25 Preferred compounds of formula XXII are of the formulas XXIIA or XXIIB:



with n being 1, 2, 3, 4, 5, 6 or 7 and Y^{211} being F, Cl, CF_3 or OCF_3 . More preferred are compounds of formula XXIIB with n being 2, 3, 4, 5, 6 or 7 and Y^{221} being F.

It is further preferred that the liquid crystal composition for the use of the invention is a nematic liquid crystal composition.

5 It will be acknowledged by those skilled in the art that the liquid crystal composition for the use according to the invention may also comprise further (mesogenic) compounds besides those disclosed in more detail in this specification. A wide variety of mesogenic compounds may be used as long as they are not detrimental to the set of parameters important for the
10 use of the bistable liquid crystal composition according to the invention.

A further subject matter of this invention is a liquid crystal medium comprising

- 15 ▪ at least at least 30 weight% (based on the total weight of the composition) of a component (α) containing one or more compounds having a dielectric anisotropy $\Delta\epsilon$ of at least 25, whereby at least 25 weight% (based on the total weight of the composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and
- 20 ▪ a component (δ) containing one or more compounds each having a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s (wherein γ_1 is the rotational viscosity at 20 °C in mPa·s and T_{NI}^K is the clearing point in degrees Kelvin).

25

A still further subject matter of the present invention is a liquid crystal medium comprising

- at least one compound of formula I; and
- at least one compound of formula II.

30

Said medium optionally comprises at least one compound of formula IV as defined above.

Still a further subject matter of the present invention is a liquid crystal medium comprising

- at least one compound of formula I; and
- 5 ▪ at least one compound of formula III.

Said medium optionally comprises at least one compound of formula IV as defined above.

10 The liquid crystal composition for use in the zenithal bistable nematic devices of the invention may also contain an optically active component (ζ) as a dopant in an amount of 0 to 3 weight%. The chiral dopant may be useful to remove reverse twist domains in the TN mode. There exists a wide variety of compounds suitable as members of component (ζ) all of which are readily available. Exemplary substances are

15 cholesterylnonanoate (CN), S-811, S-1011 and S-2011 and CB15 (Merck KGaA, Darmstadt, Germany). Although S-811 might be a preferred dopant, the specific choice of the dopants is not a critical issue.

20 The liquid crystal composition for use in the zenithal bistable nematic devices of the invention may also contain one or more light stabilizers and/or additives like pleochromatic dyes known in the state of the art.

25 All the compounds used in the liquid crystal composition of the bistable liquid crystal devices are either commercially available or can be readily prepared by methods known to those skilled in the art and as described in the standard text books of organic synthesis, for instance, in Houben-Weyl, *Methoden der Organischen Chemie*, Georg-Thieme-Verlag, Stuttgart. The liquid crystal composition will be prepared by applying standard protocols and techniques. In general, the desired amount of the minor component(s)

30 will be dissolved in the major component, usually under elevated temperature. Alternatively, solutions of components in organic solvents like acetone, chloroform or methanol, can be mixed and afterwards the


solvent(s) can be removed, e.g., by distillation. Likewise, manufacturing of the bistable devices according to the invention will follow standard techniques known to the artisan.

5 In the present description and the following examples the structures of the mesogenic compounds disclosed are described by using acronyms. Said acronyms can be transformed into chemical formulas according to Tables A and B. In these tables, radicals C_nH_{2n+1} and C_mH_{2m+1} are straight-chain alkyl radicals having n and m carbon atoms, respectively. Alkenyl radicals have the trans configuration. The codes according to Table B are self-evident. In Table A, only the acronym for the parent structure is given. In individual cases, the acronym for the parent structure is followed, usually separated by a hyphen, by a code for the substituents R^1 , R^2 , L^1 and L^2 as given below:


Code of R^1 , R^2 , L^1 , L^2	R^1	R^2	L^1	L^2
n	C_nH_{2n+1}	CN	H	H
nm	C_nH_{2n+1}	C_mH_{2m+1}	H	H
nOm	C_nH_{2n+1}	OC_mH_{2m+1}	H	H
nF	C_nH_{2n+1}	F	H	H
nN.F	C_nH_{2n+1}	CN	F	H
nN.F.F	C_nH_{2n+1}	CN	F	F

Table A:

5




PTP




CPTP

10




ME




HP

15




PCH




CCPC

20




PDX




D

25



PYP




K6


30

Table B:


5





10




15





20




25




30






PGU-n-F




CDU-n-F

5




CCGU-n-F

10




CCOC-n-m

15




PP-n-mVp




CVCP-nV-(O)m

20




PTP-n-(O)m



CPTP-n-(O)m

25











PPTUI-n-m






30


Table C:

Table C shows dopants optionally present in the liquid crystal compositions for use in the zenithal bistable nematic devices of the invention (component (5)).


**C 15****CB 15****CM 21****R/S-811****CM 44****CM 45****CM 47****R/S-1011**

- 70 -


**R/S-3011****CN****R/S-2011****R/S-4011****R/S-5011**




5




10



15




20




25

30


5




10




15






20










25





30






- 75 -

5



10



15

20

25

30

Percentages given herein are weight% and generally related to the total amount of a composition or mixture except stated otherwise. Temperatures are given in degree Celsius (°C) unless stated otherwise. T_{NI} means the clearing point at which a nematic medium becomes isotropic. Δn is the optical anisotropy (birefringence) (at 589 nm, 20 °C). $\Delta \epsilon$ means the dielectric anisotropy (at 1 kHz, 20 °C). K_1 is the splay elastic constant, and K_3 is the bend elastic constant both given in pN. Electrooptical data has been determined in a VAN zenithal bistable nematic cell. Except stated otherwise the measurements have been performed at 20 °C. V_{opt} is the corrected operating voltage (in V) derived from the corrected switching field $E_{LC@100\mu s}$ (at 25 °C; in zenithal bistable test cells with the actual cell gap d of about 2.8 to about 5 μm ; 100 μs pulse) by $V_{opt} = E_{LC@100\mu s} \cdot d_{opt}$ (with d_{opt} (in μm) being $\lambda \sqrt{3}/(2\Delta n)$; $\lambda = 555$ nm). ΔV_{opt} is the corrected operating window at a 400 μs pulse for B-W-switching and reverse switching (in V); it is calculated from the experimental switching field window $\Delta E_{LC@400\mu s}$ (at 25 °C; 400 μs pulse) multiplied with d_{opt} defined as given above. Optical response time τ_{opt} (in ms) is calculated from $\tau_{opt} = \tau \cdot d_{opt}^2/d^2$ with τ being the experimental response time, d_{opt} being as defined above and d being the experimental cell gap.

The following Examples should further illustrate the present invention as described above and in the claims but not meant to restrict its scope.

Examples

Test samples were prepared by weighing out the appropriate weight amounts (percentage weight/weight) of the individual components. The sample was then homogenised by heating into the isotropic phase and thoroughly mixing. The mixture was then stirred with a given concentration of alumina and then filtered ($0.2\mu\text{m}$) to just leave the liquid crystal mixture. The nematic to isotropic transition temperature (or clearing point, T_{NI}), dielectric anisotropy ($\Delta\epsilon$), birefringence (Δn), splay and bend elastic constants (K_1 and K_3), and rotational viscosities (γ_1) were determined as described in the Merck brochure "Physical Properties of Liquid Crystals – Description of the measurement methods", ed. W. Becker (1998). Values for single compounds are extrapolated from those determined using a known concentration (usually 10 weight% of the single compound) in a standard host mixture for which the initial mixture values are also known. The electrooptical performance of each mixture in a zentihal bistable nematic device was measured using a simple experimental set-up and the VAN type test cells. This required a transmissive mode microscope with a mounted photo-detector connected to an oscilloscope. This allowed the transmission through crossed polarisers to be monitored. The test cell was mounted on a heating stage under the microscope to permit measurements at 25°C . Bipolar electrical pulses (of varying duration and voltage) were used to ensure that there was no net d.c. voltage applied to the cell. The trailing edge (and so polarity) of each pulse therefore determined the final switched state (depending on the duration and voltage). Two signal generators were necessary to ensure that the correct initial state is first selected, with the first signal triggering the second (with an appropriate phase difference). Both signals were amplified by passing the output of the signal generators through an amplifier before being connected to the test cell. For the B-W transition, the voltages required for 10 and 90% transmission changes and reverse 90 and 10% transmission changes were

measured for various pulse durations. For the W-B transition, the voltages required for 90 and 10% transmission changes only were measured for various pulse durations. These levels were set on the oscilloscope once the 0 and 100% transmission levels were known (i.e. black and white), and they could also be used to determine the optical response time of the transition (for 10 to 90% transmission changes).

VAN type test cells were used with cell gaps typically 3-5 μ m, in transmissive mode and with crossed polarisers. Due to the varying cell thicknesses and different mixture Δn values, the retardation was not optimised but this is not crucial as it only decreases the contrast.

Example 1

5	Compound	Amount (wt%)	T_{NI} (°C)	95.0
	ME2N.F	10	$\Delta\epsilon$	46.5
	ME3N.F	10	Δn	0.1682
	ME4N.F	10	K_1 (pN)	9.2
	ME5N.F	10	K_3 (pN)	19.1
10	PZU-V2-N	10	V_{opt} (V)	13.8
	CPTP-301	5	ΔV_{opt} (V)	3.9
	CPTP-302	5	τ_{opt} (ms)	28
	CPTP-303	5		
	CCG-V-F	10		
15	CCP-V-1	10		
	CCP-V2-1	5		
	CVCP-V-O1	5		
	CVCP-1V-O1	5		
	<i>Total</i>	100		

20

25

30

Example 2

Compound	Amount (wt%)	T_{NI} (°C)	91.9
ME2N.F	12	$\Delta\epsilon$	45.3
ME3N.F	12	Δn	0.1714
ME4N.F	12	K ₁ (pN)	9.2
ME5N.F	12	K ₃ (pN)	19.0
HP-3N.F	5	V _{opt} (V)	19.7
HP-4N.F	5	ΔV_{opt} (V)	9.0
HP-5N.F	5	τ_{opt} (ms)	25
CC-5-V	12		
CCP-V-1	10		
CPTP-301	5		
CPTP-302	5		
CPTP-303	5		
<i>Total</i>	100		

Example 3

Compound	Amount (wt%)	T_{NI} (°C)	95.8
ME2N.F	10	$\Delta\epsilon$	48.0
ME3N.F	10	Δn	0.1816
ME4N.F	10	K ₁ (pN)	10.9
ME5N.F	10	K ₃ (pN)	18.8
PZU-V2-N	10	V _{opt} (V)	16.0
CPTP-301	5	ΔV_{opt} (V)	8.6
CPTP-302	5	τ_{opt} (ms)	8
CPTP-303	5	γ_1 (mPa.s)	341
CCP-V-1	15		
CCP-V2-1	15		
PPTUI-3-2	5		
<i>Total</i>	100		

- 81 -

Example 4

	Compound	Amount (wt%)	T_{NI} (°C)	90.9
	ME2N.F	9	$\Delta\epsilon$	45.2
	ME3N.F	9	Δn	0.2471
5	ME4N.F	9	K_1 (pN)	11.6
	ME5N.F	9	K_3 (pN)	14.6
	PZU-V2-N	9	V_{opt} (V)	26.4
	PPTUI-3-2	20	τ_{opt} (ms)	1
	PPTUI-3-4	25	γ_1 (mPa.s)	361
10	CCP-V-1	5		
	CCP-V2-1	5		
	<i>Total</i>	100		

Example 5

	Compound	Amount (wt%)	T_{NI} (°C)	97.1
15	ME2N.F	10	$\Delta\epsilon$	47.8
	ME3N.F	10	Δn	0.1569
	ME4N.F	10	K_1 (pN)	11.3
	ME5N.F	10	K_3 (pN)	19.4
	PZU-V2-N	10	V_{opt} (V)	8.7
20	CCPC-33	5	τ_{opt} (ms)	11
	CCPC-34	5	γ_1 (mPa.s)	407
	CCPC-35	5		
	CCP-V-1	15		
	CCP-V2-1	15		
	PPTUI-3-2	5		
25	<i>Total</i>	100		

Example 6

5	Compound	Amount (wt%)	T_{NI} (°C)	96.7
	ME2N.F	12	$\Delta\epsilon$	48.3
	ME3N.F	12	Δn	0.1674
	ME4N.F	12	K_1 (pN)	10.0
	ME5N.F	12	K_3 (pN)	20.7
10	HP-3N.F	5	V_{opt} (V)	12.8
	HP-4N.F	5	ΔV_{opt} (V)	28.6
	HP-5N.F	5	τ_{opt} (ms)	17
	CCP-V-1	16	γ_1 (mPa.s)	433
	CCP-V2-1	16		
	PPTUI-3-2	5		
	Total	100		

Example 7

15	Compound	Amount (wt%)	T_{NI} (°C)	90.0
	ME2N.F	10	$\Delta\epsilon$	57.3
	ME3N.F	10	Δn	0.1816
	ME4N.F	10	K_1 (pN)	8.4
	ME5N.F	10	K_3 (pN)	16.1
20	PZU-V2-N	10	V_{opt} (V)	11.7
	HP-3N.F	5	ΔV_{opt} (V)	8.5
	HP-4N.F	5	τ_{opt} (ms)	18
	HP-5N.F	5		
	CC-5-V	9		
25	CCP-V-1	4		
	CCP-V2-1	4		
	CPTP-301	5		
	CPTP-302	5		
	CPTP-303	5		
30	PPTUI-3-2	3		
	Total	100		

Example 8

	Compound	Amount (wt%)	T_{NI} (°C)	93.5
	ME2N.F	10	$\Delta\epsilon$	48.4
	ME3N.F	10	Δn	0.1528
5	ME4N.F	10	K ₁ (pN)	10.5
	ME5N.F	10	K ₃ (pN)	20.1
	PZU-V2-N	10	V _{opt} (V)	8.7
	CC-5-V	6	ΔV_{opt} (V)	7.3
	CCP-V-1	10	τ_{opt} (ms)	20
10	CCP-V2-1	10		
	CBC-33F	4		
	CBC-53F	4		
	CBC-55F	4		
	CBC-33	4		
	CBC-53	4		
15	CBC-55	4		
	<i>Total</i>	100		

20

25

30

Example 9

5	Compound	Amount (wt%)	T_{NI} (°C)	93.4
	ME2N.F	10	$\Delta\epsilon$	72.0
	ME3N.F	10	Δn	0.1842
	ME4N.F	10	K_1 (pN)	7.1
	ME5N.F	10	K_3 (pN)	16.7
10	PZU-V2-N	15	V_{opt} (V)	10.6
	HP-3N.F	5	ΔV_{opt} (V)	8.5
	HP-4N.F	5	τ_{opt} (ms)	27
	HP-5N.F	5		
	CCP-V-1	8		
15	CCP-V2-1	7		
	CPTP-301	5		
	CPTP-302	5		
	CPTP-303	5		
	<i>Total</i>	100		

20

25

30

Example 10

Compound	Amount (wt%)	T_{NI} (°C)	90.7
ME2N.F	10	$\Delta\epsilon$	45.9
ME3N.F	10	Δn	0.1569
ME4N.F	10	K_1 (pN)	9.9
ME5N.F	10	K_3 (pN)	18.1
PZU-V2-N	10	V_{opt} (V)	11.4
CCP-V-1	15	ΔV_{opt} (V)	11.2
CCP-V2-1	15	τ_{opt} (ms)	17
PPTUI-3-2	5	γ_1 (mPa.s)	290
CVCP-V-1	5		
CVCP-V-O1	5		
CVCP-1V-O1	5		
Total	100		

Example 11

Compound	Amount (wt%)	T_{NI} (°C)	95.9
ME2N.F	10	$\Delta\epsilon$	51.2
ME3N.F	10	Δn	0.1639
ME4N.F	10	K_1 (pN)	10.8
ME5N.F	10	K_3 (pN)	18.2
PZU-V2-N	10	V_{opt} (V)	10.7
CCP-V-1	15	τ_{opt} (ms)	17
CCP-V2-1	15		
PPTUI-3-2	5		
CBC-33F	5		
CBC-53F	5		
CBC-55F	5		
Total	100		

Example 12

Compound	Amount (wt%)	T_{NI} (°C)	91.3
ME2N.F	10	$\Delta\epsilon$	55.8
ME3N.F	10	Δn	0.1801
ME4N.F	10	K_1 (pN)	9.7
ME5N.F	10	K_3 (pN)	15.3
PZU-V2-N	14	V_{opt} (V)	17.4
CCP-V-1	8	ΔV_{opt} (V)	9.5
CCP-V2-1	8	τ_{opt} (ms)	33
PPTUI-3-2	5		
CPTP-301	5		
CPTP-302	5		
CPTP-303	5		
CC-5-V	4		
CCPC-33	2		
CCPC-34	2		
CCPC-35	2		
<i>Total</i>	100		

Example 13

5	Compound	Amount (wt%)	T_{NI} (°C)	96.2
	ME2N.F	12	$\Delta\epsilon$	47.3
	ME3N.F	12	Δn	0.1737
	ME4N.F	12	K_1 (pN)	9.8
	ME5N.F	12	K_3 (pN)	20.4
10	HP-3N.F	5	V_{opt} (V)	17.0
	HP-4N.F	5	τ_{opt} (ms)	18
	HP-5N.F	5		
	CCP-V-1	10		
	CCP-V2-1	10		
15	CBC-33F	3		
	CBC-53F	3		
	CBC-55F	3		
	PTP-201	4		
	PTP-301	4		
	<i>Total</i>	100		

20

25

30

Example 14

5	Compound	Amount (wt%)	T_{NI} (°C)	95.3
	PZU-V2-N	10	$\Delta\epsilon$	49.2
	ME2N.F	10	Δn	0.1420
	ME3N.F	10	K_1 (pN)	9.7
	ME4N.F	10	K_3 (pN)	17.1
10	ME5N.F	10	V_{opt} (V)	8.6
	CCPC-33	4	τ_{opt} (ms)	30
	CCPC-34	4		
	CCPC-35	4		
	CCP-V-1	8		
15	CCP-V2-1	8		
	CC-5-V	10		
	CBC-33F	4		
	CBC-35F	4		
	CBC-55F	4		
	Total	100		

Example 15

20	Compound	Amount (wt%)	T_{NI} (°C)	97.3
	ME2N.F	10	$\Delta\epsilon$	34.3
	ME3N.F	10	Δn	0.1393
	ME4N.F	10	K_1 (pN)	10.8
	ME5N.F	10	K_3 (pN)	17.9
25	ME7N.F	10	V_{opt} (V)	14.4
	CCPC-33	4	τ_{opt} (ms)	24
	CCPC-34	4		
	CCPC-35	4		
	CCP-V-1	6		
30	CCP-V2-1	6		
	CC-5-V	14		
	CBC-33F	4		
	CBC-35F	4		
	CBC-55F	4		
	Total	100		

Example 16

	Compound	Amount (wt%)	T_{NI} (°C)	85.6
	PZU-V2-N	20	$\Delta\epsilon$	44.2
	ME3N.F.F	10	Δn	0.1106
5	CDU-2-F	10	K ₁ (pN)	9.1
	CDU-3-F	10	K ₃ (pN)	17.9
	CDU-5-F	10	V _{opt} (V)	5.9
	CC-5-V	5	ΔV_{opt} (V)	33.5
	CCP-V-1	10	τ_{opt} (ms)	34
10	CCP-V2-1	10		
	CCPC-33	5		
	CCPC-34	5		
	CCPC-35	5		
	<i>Total</i>	100		

Example 17

	Compound	Amount (wt%)	T_{NI} (°C)	95.5
	PZU-V2-N	20	$\Delta\epsilon$	54.3
	ME3N.F.F	10	Δn	0.1741
	PGU-2-F	10	K ₁ (pN)	9.3
20	PGU-3-F	10	K ₃ (pN)	17.0
	PGU-5-F	10	V _{opt} (V)	5.6
	CCP-V-1	15	ΔV_{opt} (V)	21.1
	CCP-V2-1	10	τ_{opt} (ms)	17
	CCPC-33	5		
	CCPC-34	5		
25	CCPC-35	5		
	<i>Total</i>	100		

Example 18

	Compound	Amount (wt%)	T_{NI} (°C)	92.2
	PZU-V2-N	20	$\Delta\epsilon$	47.2
	ME2N.F	7	Δn	0.1341
5	ME3N.F	6	K_1 (pN)	10.3
	ME4N.F	4	K_3 (pN)	18.3
	ME5N.F	3	V_{opt} (V)	7.8
	CDU-2-F	5	τ_{opt} (ms)	21
	CDU-3-F	5		
	CDU-5-F	5		
10	PP-1-2V1	6		
	CCP-V-1	12		
	CCP-V2-1	12		
	CCPC-33	5		
	CCPC-34	5		
15	CCPC-35	5		
	Total	100		

Example 19

	Compound	Amount (wt%)	T_{NI} (°C)	106.2
	PZU-V2-N	19	$\Delta\epsilon$	57.4
	ME2N.F	5	Δn	0.1534
20	ME3N.F	5	K_1 (pN)	7.8
	ME4N.F	5	K_3 (pN)	12.7
	ME5N.F	5	V_{opt} (V)	6.5
	PGU-2-F	5	ΔV_{opt} (V)	31.1
	PGU-3-F	5	τ_{opt} (ms)	29
	PGU-5-F	5		
25	CCGU-3-F	5		
	CCP-V-1	13		
	CCP-V2-1	13		
	CCPC-33	5		
	CCPC-34	5		
30	CCPC-35	5		
	Total	100		

Example 20

5	Compound	Amount (wt%)	T_{NI} (°C)	91.7
	PZU-V2-N	15	$\Delta\epsilon$	39.0
	ME2N.F	5	Δn	0.1195
	ME3N.F	5	K_1 (pN)	10.3
	ME4N.F	5	K_3 (pN)	17.3
10	ME5N.F	5	V_{opt} (V)	5.4
	CDU-2-F	5	ΔV_{opt} (V)	19.6
	CDU-3-F	5	τ_{opt} (ms)	30
	CDU-5-F	5		
	CCGU-3-F	5		
15	CCP-V-1	15		
	CCP-V2-1	15		
	CCOC-3-3	5		
	CCOC-3-5	5		
	CCOC-4-3	5		
	Total	100		

Example 21

20	Compound	Amount (wt%)	T_{NI} (°C)	102.5
	PZU-V2-N	20	$\Delta\epsilon$	47.8
	ME2N.F	5	Δn	0.1462
	ME3N.F	5	K_1 (pN)	12.1
	ME4N.F	5	K_3 (pN)	20.2
25	ME5N.F	5	V_{opt} (V)	5.9
	CCGU-3-F	5	ΔV_{opt} (V)	30.6
	PP-1-2V1	10	τ_{opt} (ms)	16
	CCP-V-1	15		
	CCP-V2-1	15		
30	CCPC-33	5		
	CCPC-34	5		
	CCPC-35	5		
	Total	100		

Example 22

5	Compound	Amount (wt%)	T_{NI} (°C)	84.7
	PZU-V2-N	25	$\Delta\epsilon$	40.5
	PCH-3N.F.F	5	Δn	0.1532
	PGU-2-F	10	K ₁ (pN)	10.0
	PGU-3-F	10	K ₃ (pN)	16.8
10	PGU-5-F	10	V _{opt} (V)	6.1
	CCP-V-1	15	ΔV_{opt} (V)	7.8
	CCP-V2-1	10	τ_{opt} (ms)	34
	CCPC-33	5		
	CCPC-34	5		
15	CCPC-35	5		
	<i>Total</i>	100		


Comparative Example

MLC-6204 (Merck KGaA, Darmstadt) was tested under similar conditions as the Examples according to the invention:

20	T _{NI} (°C)	62.4
	$\Delta\epsilon$	35.2
	Δn	0.1484
	K ₁ (pN)	7.5
	K ₃ (pN)	14.8
25	V _{opt} (V)	11.8
	ΔV_{opt} (V)	7.3
	τ_{opt} (ms)	41
	γ_1 (mPa.s)	358


Claims

1. Use of a liquid crystal composition in a liquid crystal device said composition comprising
- 5
- at least 30 weight% (based on the total weight of the composition) of a component (α) containing one or more compounds having a dielectric anisotropy $\Delta\epsilon$ of at least 25, whereby at least 25 weight% (based on the total weight of the composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and
 - a component (δ) containing one or more compounds each having a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s (wherein γ_1 is the rotational viscosity at 20 °C in mPa·s and T_{NI}^K is the clearing point in degrees Kelvin).
- 10
- 15
2. Use of a liquid crystal composition according to claim 1 whereby said liquid crystal device is a zenithal bistable nematic liquid crystal device.
- 20
3. Use of a liquid crystal composition according to any one of claims 1 or 2 whereby said component (δ) comprises at least one compound of formula I
- 25




in which

R^{11} and R^{12} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;



in which


L^{11} and L^{12} are independently of each other H or F; and




in which

L^{13} and L^{14} are independently of each other H or F.

4. Use of a liquid crystal composition according to any one of claims 1 to 3 whereby said component (a) comprises at least one compound of formula II and/or at least one compound of formula III



II



III

in which


a, b, c and d are independently of each other 0, 1, 2, 3 or 4;

R^{21} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

R^{31} is C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Z^{21} and Z^{31} are independently of each other a single bond or -C≡C-.

5. Use of a liquid crystal composition according to claim 4 whereby said component (a) comprises at least one compound of formula IV



in which


e and f are independently of each other 0, 1, 2, 3 or 4;

R^{41} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


Z^{41} is a single bond or -C≡C-.

6. Use of a liquid crystal composition according to any one of claims 3 to 5 whereby in formula I


R^{11} is C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, $-C\equiv C-$, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;




is




; and




is




7. Use of a liquid crystal composition according to any one of claims 1 to 6 whereby said liquid crystal composition further comprises at least 5 weight% (based on the total weight of the composition) of a component (β) comprising at least one compound selected from the group consisting of compounds of formula V, VI, VII, VIII and IX




V




VI



VII



VIII



IX


in which

g is 0 or 1;


R^{51} , R^{52} , R^{61} , R^{62} , R^{71} , R^{72} , R^{81} , R^{82} , R^{91} and R^{92} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

L^{51} is H or F;

Z^{61} is -CO-O-, -CH₂O-, -OCH₂-, -CF₂O-, -OCF₂-, -CH₂CH₂-, -CF₂CF₂-, -CH₂CF₂-, -CF₂CH₂-, -CH=CH- or -C≡C-;




and



are independently of each other


or




;



is




or




;



is



or



;


in which

L^{52} and L^{53}

are independently of each other H or F.

8. Use of a liquid crystal composition according to any one of claims 1 to 7 whereby said liquid crystal composition further comprises at least 3 weight% (based on the total weight of the composition) of a component (γ) containing one or more compounds having an optical anisotropy Δn of at least 0.20.


9. Use of a liquid crystal composition according to claim 8 whereby said component (γ) comprises at least one compound of formula X




in which

k is 0, 1 or 2;


R^{101} and R^{102} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced by -O-, -S-, -CH=CH-, -C \equiv C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other; and




- 25 10. Use of a liquid crystal composition according to any one of claims 3 to 9 whereby said liquid crystal composition further comprises at least one compound of formula XI and/or at least one compound of formula XII and/or at least one compound of formula XIII at least one compound of formula XIV




XI



XII



XIII



XIV

in which

R^{111} and R^{142} are independently of each other C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

R^{121} , R^{131} , R^{132} and R^{141} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


R^{122} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Y^{111} is F or Cl;

L^{111} and L^{112} are independently of each other H or F; and




and




are independently of each

other



or



5

10

15

20

25








30

11. Use of a liquid crystal composition according to any one of claims 1 to 10 whereby said liquid crystal composition comprises at least 50 weight% (based on the total weight of the composition) of said component (α).

12. Use of a liquid crystal composition according to any one of claims 1 to 11 whereby said liquid crystal composition comprises at least 50 weight% (based on the total weight of the composition) of said component (α) whereby at least 30 weight% (based on the total weight of the composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40.

13. Use of a liquid crystal composition according to any one of claims 1 to 12 whereby said liquid crystal composition comprises at least 5 weight% (based on the total weight of the composition) of said component (δ).

14. Use of a liquid crystal composition according to any one of claims 1 to 13 whereby said liquid crystal composition comprises at least one compound of formula XVI and/or XVII and/or of formula XVIII and/or of formula XIX and/or of formula XX and/or of formula XXI and/or of formula XXII:



in which

$R^{161}, R^{171}, R^{181}, R^{182}, R^{201}, R^{211}$ and R^{221}

are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C \equiv C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

R^{191}

is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -C \equiv C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

$Y^{161}, Y^{171}, Y^{191}, Y^{201}, Y^{211}$ and Y^{221}

are independently of each

other F, Cl, C_1 - C_{15} alkanyl or C_2 - C_{15} alkenyl that are independently of each other mono- or poly-substituted with halogen, or C_1 - C_{15} alkoxy, which is mono- or poly-substituted with halogen;

$L^{161}, L^{171}, L^{191}, L^{192}, L^{201}, L^{202}, L^{203}, L^{204}, L^{211}, L^{212}, L^{213}, L^{214}, L^{215}, L^{216}, L^{221}, L^{222}, L^{223}$ and L^{224}

are independently of each other H or F;

and

Z^{161}


is -CO-O-, CH_2O or CF_2O .

15. Liquid crystal medium comprising

- at least 30 weight% (based on the total weight of the composition) of a component (α) containing one or more compounds having a dielectric anisotropy $\Delta\epsilon$ of at least 25,
whereby at least 25 weight% (based on the total weight of the composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and
- a component (δ) containing one or more compounds each having a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s (wherein γ_1 is the rotational viscosity at 20 °C in mPa·s and T_{NI}^K is the clearing point in degrees Kelvin).


16. Liquid crystal medium according to claim 15 whereby

- said component (δ) comprises at least one compound of formula I




in which

R^{11} and R^{12} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;



in which

L^{11} and L^{12} are independently of each other H or F; and




in which

L^{13} and L^{14} are independently of each other H or F;

and

▪ said component (α) comprises at least one compound of formula II



II

in which


a and b are independently of each other 0, 1, 2, 3 or 4;

R^{21} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Z^{21} is a single bond or -C≡C-.

17. Liquid crystal medium according to claim 15 whereby


▪ said component (δ) comprises at least one compound of formula I



I


in which

R^{11} and R^{12} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;



in which

L^{11} and L^{12} are independently of each other H or F; and




in which

L^{13} and L^{14} are independently of each other H or F;

and

- said component (α) comprises at least one compound of formula III




in which

c and d are independently of each other 0, 1, 2, 3 or 4;

R^{31} is C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Z^{31} is a single bond or -C≡C-.

18. Liquid crystal medium according to any one of claims 16 or 17 whereby said component (α) further comprises at least one compound of formula IV



IV

in which

e and f are independently of each other 0, 1, 2, 3 or 4;

R^{41} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


Z^{41} is a single bond or -C≡C-.

19. Bistable liquid crystal device comprising

- two outer substrates which, together with a frame, form a cell;
- a liquid crystal composition present in said cell;


- 5
- electrode structures with alignment layers on the inside of said outer substrates whereby at least one alignment layer comprises an alignment grating that permits the compounds of said liquid crystal composition to adopt at least two different stable states whereby the assembly of said electrode structures with said alignment layers being such that a switching between the said at least two different stable states is achieved by applying suitable electric signals to said electrode structures;
 - whereby said liquid crystal composition comprises
 - 10
 - at least 30 weight% (based on the total weight of the composition) of a component (α) containing one or more compounds having a dielectric anisotropy $\Delta\epsilon$ of at least 25, whereby at least 25 weight% (based on the total weight of the composition) of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and
 - 15
 - a component (δ) containing one or more compounds having a ratio of γ_1/T_{NI}^K of 0.51 mPa·s/K or less, a clearing point T_{NI} of at least 100 °C and a rotational viscosity γ_1 of not more than 190 mPa·s (wherein γ_1 is the rotational viscosity at 20 °C in mPa·s and T_{NI}^K is the clearing point in degrees Kelvin).
- 20
20. Bistable liquid crystal device according to claim 19 whereby
- said device is a zenithal bistable nematic liquid crystal device; and
 - 25
 - said electrode structures with alignment layers on the inside of said outer substrates have at least one alignment layer that comprises an alignment grating that permits the compounds of said liquid crystal composition to adopt at least two different stable states with different pretilt angles in the same azimuthal plane.
- 30

21. Bistable liquid crystal device according to any one of claims 19 or 20 whereby said component (δ) comprises at least one compound of formula I




in which

- 10 R^{11} and R^{12} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;



in which


- 20 L^{11} and L^{12} are independently of each other H or F; and




in which

- L^{13} and L^{14} are independently of each other H or F.

22. Zenithal bistable nematic liquid crystal device according to any one of claims 19 or 21 whereby said component (α) comprises at least one compound of formula II and/or at least one compound of formula III
- 30



II



III

in which


a, b, c and d are independently of each other 0, 1, 2, 3 or 4;

R²¹ is C₁-C₁₅ alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH₂ groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

R³¹ is C₂-C₁₅ alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH₂ groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Z²¹ and Z³¹ are independently of each other a single bond or -C≡C-.

23. Zenithal bistable nematic liquid crystal device according to claim 22 whereby said component (α) comprises at least one compound of formula IV



IV

in which






e and f are independently of each other 0, 1, 2, 3 or 4;

R^{41} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;

Z^{41} is a single bond or $-C\equiv C-$.

24. Zenithal bistable nematic liquid crystal device according to any one of claims 21 to 23 whereby said liquid crystal composition further comprises

- at least 5 weight% (based on the total weight of the composition) of a component (β) comprising at least one compound selected from the group consisting of compounds of formula V, VI, VII, VIII and IX




in which

g is 0 or 1;


$R^{51}, R^{52}, R^{61}, R^{62}, R^{71}, R^{72}, R^{81}, R^{82}, R^{91}$ and R^{92} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by $-O-$, $-S-$, $-CH=CH-$, $-C\equiv C-$, $-CO-O-$, $-OC-O-$ such that there are no hetero atoms adjacent to each other;

L^{51} is H or F;

Z^{61} is $-CO-O-$, $-CH_2O-$, $-OCH_2-$, $-CF_2O-$, $-OCF_2-$, $-CH_2CH_2-$, $-CF_2CF_2-$, $-CH_2CF_2-$, $-CF_2CH_2-$, $-CH=CH-$ or $-C\equiv C-$;




and



are independently of each other


or




;



is




or




;



is



or



;

in which

L^{52} and L^{53}

are independently of each other H or F.


25. Zenithal bistable nematic liquid crystal device according to any one of claims 19 to 24 whereby said liquid crystal composition further comprises

- at least 3 weight% (based on the total weight of the composition) of a component (γ) containing one or more compounds having an optical anisotropy Δn of at least 0.20.

5

26. Zenithal bistable nematic liquid crystal device according to claim 25 whereby said component (γ) comprises at least one compound of formula X

10




in which

15

k is 0, 1 or 2;

R^{101} and R^{102} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced by -O-, -S-, -CH=CH-, -C \equiv C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other; and


20




25

27. Zenithal bistable nematic liquid crystal device according to any one of claims 21 to 26 whereby said liquid crystal composition further comprises at least one compound of formula XI and/or at least one compound of formula XII and/or at least one compound of formula XIII at least one compound of formula XIV


30




XI



XII



XIII



XIV

in which


R^{111} and R^{142} are independently of each other C_2 - C_{15} alkenyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

R^{121} , R^{131} , R^{132} and R^{141} are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;


R^{122} is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Y^{111} is F or Cl;

L^{111} and L^{112} are independently of each other H or F; and




and




are independently of each


other




or




28. Bistable liquid crystal device according to any one of claims 19 to 27 whereby said liquid crystal composition comprises at least one compound of formula XVI and/or XVII and/or of formula XVIII and/or of formula XIX and/or of formula XX and/or of formula XXI and/or of formula XXII:




XVI




XVII




XVIII




XIX



XX



XXI



XXII

in which

 $R^{161}, R^{171}, R^{181}, R^{182}, R^{201}, R^{211}$ and R^{221}

are independently of each other C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -CH=CH-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

 R^{191}

is C_1 - C_{15} alkyl which is unsubstituted or mono- or poly-substituted with CN or halogen and in which one or more of the CH_2 groups may be replaced independently of each other by -O-, -S-, -C≡C-, -CO-O-, -OC-O- such that there are no hetero atoms adjacent to each other;

Y^{161} , Y^{171} , Y^{191} , Y^{201} , Y^{211} and Y^{221} are independently of each other F, Cl, C_1 - C_{15} alkanyl or C_2 - C_{15} alkenyl that are independently of each other mono- or poly-substituted with halogen, or C_1 - C_{15} alkoxy, which is mono- or poly-substituted with halogen;

L^{161} , L^{171} , L^{191} , L^{192} , L^{201} , L^{202} , L^{203} , L^{204} , L^{211} , L^{212} , L^{213} , L^{214} , L^{215} , L^{216} , L^{221} , L^{222} , L^{223} and L^{224} are independently of each other H or F;

and

Z^{161} is $-CO-O-$, CH_2O or CF_2O .

Figures




Figure 1. Illustration of zenithal bistability using grating alignment (with the lines indicating the local director) showing a) the high tilt (continuous) and b) the low tilt (defect) states.




Figure 2. The a) VAN and b) TN geometries for ZBD showing the director distribution of the high and low tilt states.




Figure 3. The τ -V curve for MLC-6204-000 at 25°C (pulse duration or time slot vs. voltage). The switching voltage ($V_{100\mu s}$) and operating window ($\Delta V_{400\mu s}$) used for comparisons are indicated.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP 03/12952

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C09K19/46 C09K19/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	GB 2 358 870 A (MERCK PATENT GMBH) 8 August 2001 (2001-08-08) claims; examples	1,3-7, 10,14-18 2,8,9, 11-13, 19-28
X	--- DE 100 20 059 A (MERCK PATENT GMBH) 11 January 2001 (2001-01-11) claims; examples	1,3-7,9, 10,14-18
X	--- DE 100 20 061 A (MERCK PATENT GMBH) 7 December 2000 (2000-12-07) claims; examples	1,3-7,9, 10,14-18
X	--- DE 100 56 323 A (MERCK PATENT GMBH) 21 June 2001 (2001-06-21) claims	1,3-7,9, 14-18
	--- -/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

8 document member of the same patent family

Date of the actual completion of the international search

2 March 2004

Date of mailing of the international search report

08/03/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
 Fax: (+31-70) 340-3016

Authorized officer

Serbetsoglou, A

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/12952

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 100 27 066 A (MERCK PATENT GMBH) 11 January 2001 (2001-01-11) claims; examples ----	1,3-5,7, 9,14-18
X	DE 101 12 954 A (MERCK PATENT GMBH) 13 December 2001 (2001-12-13) claims ----	1,3-5,14
X	DE 100 18 598 A (MERCK PATENT GMBH) 2 November 2000 (2000-11-02) claims 1,6 ----	1,3-5,7
X	US 6 440 506 B1 (KOJIMA ET AL) 27 August 2002 (2002-08-27) claims ----	1,3-7
X	WO 01 64814 A (MERCK PATENT GMBH) 7 September 2001 (2001-09-07) claims ----	1,3-7
P,X	DE 102 29 505 A (MERCK PATENT GMBH) 13 February 2003 (2003-02-13) claims ----	1,3-5,9
P,X	DE 102 23 912 A (MERCK PATENT GMBH) 16 January 2003 (2003-01-16) claims ----	1,3-5,9
A	WO 99 34251 A (THE SECRETARY OF STATE FOR DEFENCE) 8 July 1999 (1999-07-08) claims -----	1,2,15, 19,20

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/12952

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2358870	A	08-08-2001	DE 19707807 A1 GB 2323601 A JP 10245559 A US 5976407 A	03-09-1998 30-09-1998 14-09-1998 02-11-1999
DE 10020059	A	11-01-2001	DE 10020059 A1 JP 2001011449 A US 6569503 B1	11-01-2001 16-01-2001 27-05-2003
DE 10020061	A	07-12-2000	DE 10020061 A1 JP 2001011448 A TW 538267 B US 6544602 B1	07-12-2000 16-01-2001 21-06-2003 08-04-2003
DE 10056323	A	21-06-2001	DE 10056323 A1 US 2003148043 A1 US 2002197420 A1	21-06-2001 07-08-2003 26-12-2002
DE 10027066	A	11-01-2001	DE 10027066 A1 DE 10030459 A1 JP 2001064651 A US 6514579 B1	11-01-2001 15-03-2001 13-03-2001 04-02-2003
DE 10112954	A	13-12-2001	DE 10112954 A1 JP 2001354962 A US 2003224125 A1	13-12-2001 25-12-2001 04-12-2003
DE 10018598	A	02-11-2000	DE 10018598 A1 JP 2000351972 A US 2003113482 A1	02-11-2000 19-12-2000 19-06-2003
US 6440506	B1	27-08-2002	EP 1310541 A2 EP 1002848 A1 JP 2000154383 A	14-05-2003 24-05-2000 06-06-2000
WO 0164814	A	07-09-2001	AU 2365601 A CN 1437647 T DE 10102631 A1 WO 0164814 A1 EP 1261679 A1 JP 2003525474 T	12-09-2001 20-08-2003 30-08-2001 07-09-2001 04-12-2002 26-08-2003
DE 10229505	A	13-02-2003	DE 10229505 A1 CN 1400279 A JP 2003129053 A US 2003127629 A1	13-02-2003 05-03-2003 08-05-2003 10-07-2003
DE 10223912	A	16-01-2003	DE 10223912 A1 JP 2003089789 A US 2003104143 A1	16-01-2003 28-03-2003 05-06-2003
WO 9934251	A	08-07-1999	AT 245285 T AU 1572599 A CN 1285050 T DE 69816481 D1 EP 1042702 A1 GB 2346978 A ,B WO 9934251 A1	15-08-2003 19-07-1999 21-02-2001 21-08-2003 11-10-2000 23-08-2000 08-07-1999

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP 03/12952

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9934251	A	JP 2002500383 T	08-01-2002